

GUILBERT EXPRESS

Le Pérípole, Lot 209-210 - 33 avenue du Maréchal de Lattre de Tassigny


















94127 Fontenay sous Bois Cedex - France - Tel.: + 33 1 53 99 16 98 - Fax : + 33 1 53 99 16 56

SOLDERS

Created on: 10/06/2009

Modified on: 22/10/2018

Issue: E

SDS	Ref.	Description	Quantity g or rod	Diameter mm	Length mm	Melting temperature °C	Mechanical strength daN/mm ²	FLUX Ref.	Tools and ease of implementation	Applications								
										Pipework			Metals					
										Cold / Hot Copper tube	GAS Copper tube	Air conditioning Copper tube	Iron and steels	Stainless steels	Cast iron	Brass	Light alloys	
	504050	Cu/Ph (6.3%) Special Tapping	500 g	2	500	710/845	55	050100 105100 105200	 ★★	PRE-ORDER	NO	Yes	No	No	No	Yes	No	
309	500050	Cu/Ph (6.6%) Premium	500 g	2	500	710 / 825	50	105200 105100 105200	 ★★	PRE-ORDER	No	Yes	No	No	No	Yes	No	
	1 kg																	
	5 kg																	
323	511100	Cu/Ph (6.8%) Worksite	1 kg	2	500	710 / 815	45	105200 105100 105200	 ★★★	PRE-ORDER	No	Yes	No	No	No	Yes	No	
	5 kg																	
310	501100	Cu/Ph (7.3%) - High fluidity	1 kg	2	500	710 / 785	45	050100 105100 105200	 ★★★	PRE-ORDER	No	Yes	No	No	No	Yes	No	
	501815		15 rods / 170g	2	380													
	501840		40 rods / 440g	2	380													
	509050	Cu/Ph (7.8%) AERO PROPANE	500 g	2	500	710/750	45	050100 105100 105200	 ★★★	PRE-ORDER	NO	Yes	No	No	No	Yes	No	
301	502820	Cu/Ph 2% Ag	20 rods / 270g	2	500	650 / 820	55	050100 105100 105200	 ★★★★	PRE-ORDER	NO	Yes	No	No	No	Yes	No	
302	506010	Cu/Ph 6% Ag (ATG certified) 	100 g	2	500	645 / 725	45	050100 105100	 ★★★★★	Yes	 PRE-ORDER	Yes	Yes	No	No	Yes	No	
	506050		500 g															
	506100		1 kg															
	506805		5 rods / 50g															2
305	540803	Cu/Ph 34% Ag (ATG certified) 	3 rods / 30g	2	380	630 / 710	50	050100 105100	 ★★★★★	Yes	 PRE-ORDER	Yes	Yes	Yes	No	Yes	No	
	540010		100 g	2	500													
306	508102	Coated brass	1 kg	2	500	870 / 890	45	Coated	 ★★★★★	Yes	No	No	PRE-ORDER	No	No	Yes	No	
	508103		1 kg	3	500													
	508813		10 rods / 120g	3	380													
	508812		10 rods / 240g	2	380													
320	534803	Cu/Zn 34%Ag (tubular with incorporated flux)	3 rods / 30g	2	500	630 / 730	50	Incorporated	 ★★★★★	PRE-ORDER	No	Yes	Yes	Yes	No	Yes	No	
326	541805	Cu/Zn 40%Ag (coated rods)	3 baguettes / 90g	2	500	650/710	50	Incorporated	 ★★★★★	PRE-ORDER	No	Yes	Yes	Yes	Yes	Yes	Yes	No
321	507803	Zinc solder (with incorporated flux)	3 rods / 30g	2	500	440 / 460	14	Incorporated	 ★★★★★	No	No	No	No	No	No	No	No	PRE-ORDER
307	510815	Copper coated steel wire	15 rods	1.5	500	1400	45	1840	 ★★	No	No	No	PRE-ORDER	No	No	No	No	
	510840		40 rods															